Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

Food Contact Declaration of Compliance

Declaration Identification No:	FCMD-Olympia-004

Declaration of Compliance *(tick all that apply)*

☒	On materials and articles in contact with food Regulation (EC) No 1935/2004
☒	Good Manufacturing Practices (GMP, Commission Regulation (EC) No 2023/2006)
☐	BPA and other hazardous bisphenols in materials and articles that come into contact with food Commission Regulation (EU) 2024/3190
☐	Plastic monomers and additives in Regulation 10/2011
☐	For active/intelligent materials in Regulation 450/2009
☐	For recycled plastic processes in Regulation 282/2008
☐	Fo regenerated cellulose film in The Materials and Articles in Contact with Food (England) Regulations 2012

Identification of Food Contact Material

Product Code	Description	Material Type *(e.g. PP / PET / PE / PS – as applicable)*	Intended use
C092	Olympia Vacuum Jug St/St - 1.5Ltr	SS	To keep liquids hot or cold for many hours
DL160	Olympia Vacuum Jug St/St Domed Lid - 1.5Ltr 'TEA'	SS	To keep liquids hot or cold for many hours
DL161	Olympia Vacuum Jug St/St Domed Lid - 1.5Ltr 'COFFEE'	SS	To keep liquids hot or cold for many hours
DL162	Olympia Vacuum Jug St/St Domed Lid - 1.5Ltr 'HOT WATER'	SS	To keep liquids hot or cold for many hours
DL167	Olympia Vacuum Jug St/St Double Wall hinged lid - 1Ltr 33.8fl oz	SS	To keep liquids hot or cold for many hours
DL168	Olympia Vacuum Jug St/St Double Wall hinged lid - 1.5Ltr	SS	To keep liquids hot or cold for many hours
DL169	Olympia Vacuum Jug St/St Double Wall hinged lid - 2Ltr	SS	To keep liquids hot or cold for many hours
K656	Olympia Vacuum Jug St/St Domed Lid - 1.5Ltr	SS	To keep liquids hot or cold for many hours

Composition and BPA / Bisphenol Compliance

In accordance with applicable EU bisphenol requirements:

(1) Bisphenols or bisphenol derivatives intentionally used: None ☐ / Declared below ☐

☒	None
☐	Yes, declared in (2) below

(2) Where Bisphenols or bisphenol derivatives are intentionally used:
(If applicable complete table below):

Substance name	CAS number

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

The plastic food contact article does not contain intentionally added bisphenol A (BPA) or other restricted bisphenols unless explicitly declared and legally permitted.

Where applicable, compliance with specific migration limits (SMLs) for regulated substances has been verified.

I, the undersigned, declare that the equipment specified above conforms to the Regulations as stipulated within this Declaration.

Signed by:
Ashley Hooper
AB6DB7656FFB441...

Nisbets Limited
Avonmouth, United Kingdom – [07.05.2025]
Ashley Hooper
Group Head of Product Quality & Compliance

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

Migration Testing Compliance

Migration testing has been performed or substantiated to demonstrate compliance with EU requirements:

Overall Migration:
Verified in accordance with Regulation (EU) No 10/2011, using appropriate food simulants and time/temperature conditions representative of intended use.

Specific Migration:
Specific migration limits (SMLs) for regulated substances listed in Annex I of Regulation (EU) No 10/2011 have been assessed and confirmed as compliant, where applicable.

Testing Approach:

☒	Laboratory testing by an accredited laboratory
☐	Compliance substantiated using supplier declarations and worst-case calculation
☐	Combination of testing and risk-based assessment

Test Conditions Covered *(insert screenshot of test report to satisfy the following section)*:
Simulants, contact time, and temperature conditions reflect worst-case foreseeable use of the product.

Test report:

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

1. Sensorial examination

Test method: It is examined to the extent of food simulant being used, which comes into contact with the product, undergoes detectable changes in taste and smell.
For this purpose, the food simulant was stored in the product under the below mentioned time and temperature. Afterwards, the food simulant was examined by an appropriate number of tasters with regard to any divergence in smell and taste. Another test sample, which was used as a reference, was treated by the same way except that it had no contact with the product to be tested.
Before testing, the product had been cleaned according to the product's instruction manual or in the absence of such manual, by normal household cleaning.
The test is carried out on the basis of DIN 10955:2024 by paired comparison test:

Evaluation scheme:

0 = No perceptible difference
1 = Just perceptible difference (still difficult to define)
2 = Slight difference (possible to define)
3 = Marked difference
4 = Strong difference

Limit: 3 (failed)

The following food simulants and conditions were applied:

Food simulant	Test duration / Temperature
Water	Fill with boiling water and let stand at 40°C for 24 hours

Test No.:	T001
Sample No.:	M004
Parameter:	**Result**
Transfer of Smell:	0.5
Transfer of Taste:	0.5

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

2. Global Migration

Test method: The migratory behaviour was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments.

Limit: With reference to Commission Regulation (EU) No 10/2011 and its amendments

The following food simulants and conditions were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	Fill with boiling 3% Acetic acid and let stand at 40°C for 24 hours
Ethanol 50 %	Fill with boiling 50%Ethanol and let stand at 40°C for 24 hours

Test No.:	T001					
Sample No.:	M004					
Migration ratio:	205 ml / dm^2					
Parameter	**Unit**	**RL**	**1st Migration Result**	**2nd Migration Result**	**3rd Migration Result**	**Limit**
Acetic acid 3 %	mg/dm^2	2	< RL	< RL	< RL	10
Ethanol 50 %	mg/dm^2	2	2	< RL	< RL	10

Abbreviations:

RL = Reporting Limit

mg/dm^2 = Milligram per square decimetre

ml/dm^2 = Mililitre per square decimetre

< = Less than

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

3. Specific Migration of Metals

Test method: The migratory behaviour was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments. Determination by ICP-MS.

Limit: With reference to Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition were applied:

Food simulant	Test duration / Temperature
3% Acetic acid	Fill with boiling 3% Acetic acid and let stand at 40°C for 24 hours

Test No.:	T001					
Material No.:	M004					
Migration ratio:	205 ml / dm^2					
Parameter	**Unit**	**RL**	**1st Migration Result**	**2nd Migration Result**	**3rd Migration Result**	**Limit**
Aluminium	mg/kg	0.1	n.d.	n.d.	n.d.	1
Antimony	mg/kg	0.01	n.d.	n.d.	n.d.	0.04
Arsenic	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Barium	mg/kg	0.1	n.d.	n.d.	n.d.	1
Cadmium	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Total Chromium	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Cobalt	mg/kg	0.01	n.d.	n.d.	n.d.	0.05
Copper	mg/kg	0.5	n.d.	n.d.	n.d.	5
Iron	mg/kg	5	n.d.	n.d.	n.d.	48
Lead	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Lithium	mg/kg	0.1	n.d.	n.d.	n.d.	0.6
Manganese	mg/kg	0.1	n.d.	n.d.	n.d.	0.6
Mercury	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Nickel	mg/kg	0.01	n.d.	n.d.	n.d.	0.02
Zinc	mg/kg	1	n.d.	n.d.	n.d.	5
Europium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Gadolinium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Lanthanum	mg/kg	0.01	n.d.	n.d.	n.d.	--
Terbium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Sum of Lanthanide substances	mg/kg	0.01	n.d.	n.d.	n.d.	0.05

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

Abbreviations:

RL = Reporting limit
n.d. = Not detected
mg/kg = Milligram per kilogram
ml/dm² = Mililitre per square decimetre
< = Less than

Remark:

*1 Single component with an amount below reporting limit was not considered by the calculation of the sum. In the case of all lanthanide substances europium, gadolinium, lanthanum and terbium were not detected, the result is stated n.d.

4. Specific Migration of Polycyclic Aromatic Hydrocarbons (PAHs) from silicone

Test method: The migratory behaviour was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments. Determination by GC-MS.

Limit: Please refer to remark 1

The following food simulant and condition was applied:

Food simulant	Test duration / Temperature
Ethanol 50 %	Fill boiling Ethanol 50 % and let stand at 40 °C for 24 hours

Test No.:	T001						
Material No.:	M004						
Migration ratio:	205 ml / dm²						
Parameter	**CAS No.**	**Unit**	**RL**	**1st Migration Result**	**2nd Migration Result**	**3rd Migration Result**	**Limit**
Benzo[a]pyrene (BaP)	50-32-8	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[e]pyrene	192-97-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[a]anthracene	56-55-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[b]fluoranthene	205-99-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[j]fluoranthene	205-82-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[k]fluoranthene	207-08-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
Chrysene	218-01-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
Dibenzo[a,h]anthracene	53-70-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
Benzo[g,h,i]perylene	191-24-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
Indeno[1,2,3-c,d]pyrene	193-39-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
Naphthalene	91-20-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
Anthracene	120-12-7	mg/kg	0.01	n.d.	n.d.	n.d.	-
Fluoranthene	206-44-0	mg/kg	0.01	n.d.	n.d.	n.d.	-
Phenanthrene	85-01-8	mg/kg	0.01	n.d.	n.d.	n.d.	-
Pyrene	129-00-0	mg/kg	0.01	n.d.	n.d.	n.d.	-
Sum of 15 PAHs	-	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

Abbreviations:

mg/kg	= Milligram per kilogram
n.d.	= Not detected (< Reporting Limit)
ml/dm^2	= Millilitre per square decimetre
RL	= Reporting Limit
<	= Less than

Remark:

*1 Polycyclic aromatic hydrocarbons (PAHs) are not listed substances for the production of plastic materials acc. to Regulation (EU) No. 10/2011, Annex I. A threshold of detection <0.01 mg/kg should be met.

*2 Single component with an amount below reporting limit was not considered by the calculation of the sum. In the case all of PAHs were not detected, the result is stated n.d.

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

5. Specific Migration of Primary Aromatic Amines

Test method: The migratory behaviour was examined with reference to Commission Regulation (EU) No 10/2011 and its amendments. Determination by LC-MS/MS.

Limit: With reference to Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	Fill with boiling 3% Acetic acid and let stand at 40°C for 24 hours

Test No.:		T001					
Material No.:		M004					
Migration ratio:		205 ml / dm^2					
Parameter	CAS no.	Unit	RL	1st Migration Result	2nd Migration Result	3rd Migration Result	Limit
2,4-Diaminoanisole	615-05-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2,4-toluenediamine	95-80-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-oxydianiline	101-80-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Benzidine	92-87-5	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-methylenedianiline	101-77-9	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-anisidine	90-04-0	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-Toluidine	95-53-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-bi-o-toluidine	119-93-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-chloroaniline	106-47-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
p-cresidine	120-71-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-chloro-o-toluidine	95-69-2	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-aminobiphenyl	92-67-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-Methylene-di-o-toluidine	838-88-0	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-thiodianiline	139-65-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2-Naphthylamine	91-59-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
3,3'-Dichlorobenzidine	91-94-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-aminoazobenzene	60-09-3	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-aminoazotoluene	97-56-3	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2,4,5-Trimethylaniline	137-17-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2-Methyl-5-nitroaniline	99-55-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
m-phenylenediamine	108-45-2	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Benzoguanamine	91-76-9	mg/kg	0.01	n.d.	n.d.	n.d.	5
4,4'-Methylenebis-(3-cholor-2,6-diethylaniline)	106246-33-7	mg/kg	0.01	n.d.	n.d.	n.d.	0.05
PAAs not listed in entry 43 to Appendix 8 of Annex XVII to Regulation (EC) No 1907/2006 and its amendments							
p-toluidine	106-49-0	mg/kg	0.01	n.d.	n.d.	n.d.	-
p-phenylenediamine	106-50-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Methyl-4-nitroaniline	99-52-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
o-phenylenediamine	95-54-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
1,5-naphthylenediamine	2243-62-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
Aniline	62-53-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4-Dimethylaniline	95-68-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,6-Dimethylaniline	87-62-7	mg/kg	0.01	n.d.	n.d.	n.d.	-
5-Chloro-2-methylaniline	95-79-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,6-toluenediamine	823-40-5	mg/kg	0.01	n.d.	n.d.	n.d.	-

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

5-Amino-6-methyl-1,3-dihydro-2H-benzimidazol-2-one	67014-36-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-aminobenzamide	2835-68-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Amino-4-methylbenzamide	19406-86-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
m-Anisidine	536-90-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
m-toluidine	108-44-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Ethoxyaniline	156-43-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-ethoxyaniline	94-70-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Chloro-3-methoxyaniline	13726-14-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
1,3-Diiminoisoindoline	3468-11-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Amino-4-methoxybenzanilide	120-35-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4,5-Trichloroaniline	636-30-6	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-chloro-2,5-dimethoxyaniline	6358-64-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Methoxy-4-nitroaniline	97-52-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
5-Chloro-2-methoxyaniline	95-03-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Chloroaniline	108-42-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Chloroaniline	95-51-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
Dimethyl-2-aminoterephthalate	5372-81-6	mg/kg	0.01	n.d.	n.d.	n.d.	-
Biphenyl-2-ylamine	90-41-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,5-Dichloroaniline	95-82-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Nitroaniline	88-74-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Aminotoluene-3-sulfonic acid	88-44-8	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Aminonaphthalene-1-sulfonic acid	81-16-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4-Dinitroaniline	97-02-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Chloro-4-nitroaniline	121-87-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
Sum of Primary Aromatic Amines"[1]	-	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Abbreviations:
RL = Reporting Limit
n.d. = Not detected
mg/kg = Milligram per kilogramm
ml/dm² = Mililitre per square decimetre
< = Less than

6. Volatile Organic Substances (Silicone)

Test method: The test was performed according to the Bestimmung von flüchtigen Verbindungen in Bedarfsgegenständen aus Silikon.

Limit: BfR Recommendations on Food Contact Materials (formerly "Plastics Recommendations") Part XV, Silicones

The following conditions were applied:

Test duration / Temperature
200°C for 4 hours

Test No.:	T001			
Material No.:	M006			
Parameter	**Unit**	**RL**	**Result**	**Limit**
Volatile organic substances (VOC)	%	0.1	< RL	0.5

Abbreviations:
% = Percentage
< = Less than
RL = Reporting Limit

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

7. Remaining Peroxides (Silicone)

Test method: The test was performed with reference to the 58th Communication on testing of plastics, Bundesgesundheitsbl. 40 (1997) 412

Limit: BfR Recommendations on Food Contact Materials (formerly "Plastics Recommendations") Part XV "Silicone"

Test No.:	T001			
Sample No.:	M006			
Parameter	**Unit**	**RL**	**Result**	**Limit**
Peroxides	%	0.01	n.d.	n.d.

Abbreviations:

% = Percentage
RL = Reporting Limit
n.d. = Not detected (<Reporting Limit)
< = Less than

8. Residual Catalyst

Test method: The synthetic material is dissolved by acid digestion. The concentration of platinum was determined by means of ICP-OES.

Limit: BfR Recommendations on Food Contact Materials (formerly "Plastics Recommendations") Part XV, "Silicones"

Test No.:	T001			
Sample No.:	M006			
Parameter	**Unit**	**RL**	**Result**	**Limit**
Platinum	mg/kg	10	n.d.	50

Abbreviations:

n.d. = Not detected (<Reporting Limit)
RL = Reporting Limit
mg/kg = Milligram per kilogram

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

9. Colourfastness

Test method: 24th Communication on the testing of plastics in Bundesgesundheitsbl. 15 (1972) 285

Requirement: BfR Recommendations on Food Contact Materials (formerly "Plastics Recommendations") Part IX "Colorants for Plastics and other Polymers used in Commodities" - *No transfer of colorants to foodstuffs is permitted*

Test No.:	T001
Sample No.:	M007
Parameter – Colourfastness to	**Difference between blank and filter paper contacted with sample**
Water	No
Acetic acid 3 %	No
Ethanol 50 %	No
Oil	No

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

10. Release of Heavy Metals from Glassware

Test method: The test is performed reference to EN 1388-1:1995, EN 1388-2:1995 and DIN 51031:1986 respectively. The concentration of the elements is examined by means of atomic absorption spectroscopy or ICP-MS.

Limit:
- Pb, Cd: Directive 84/500/EEC
- Co: Working group of food chemistry experts from the federal states and the Federal Office of Consumer Protection and Food Safety (ALS), 109th Session 2017, Opinion No.2017/15
- Zn, Ba, Sb: Austrian Ceramic Ordinance

The following food simulant and condition was applied:

Food simulant	Test duration / Temperature
4% Acetic acid	22°C for 24 hours

Test No.:	T001		
Category:	2		
Internal volume	Less than one litre		
Sample No.:	M005		
Parameter	**Unit**	**Result**	**Limit** (*1,2)
Lead (Pb)	mg/l	< 0.2	4.0
Cadmium (Cd)	mg/l	< 0.02	0.3
Cobalt (Co)	mg/l	< 0.05	0.1
Zinc (Zn)	mg/article	< 0.5	3.0
Barium (Ba)	mg/article	< 0.5	1.0
Antimony (Sb)	mg/article	< 0.5	1.0

Abbreviations:

mg/dm^2 = Milligram per square decimetre
mg/article = Milligram per article
mg/l = Milligram per litre
< = Less than

Docusign Envelope ID: 1811EF77-48FD-8497-8160-6BF77BAA4910

OLYMPIA

Olympia Tableware, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@olympia-tableware.com

Remarks:

*1 According to EU Directive 84/500/EEC, articles in contact with food should not exceed the following limits

Category	Description	Lead	Cadmium
1	Articles which can't and articles which can be filled, the internal depth of which, measured from the lowest point to the horizontal plane passing through the upper rim, does not exceed 25 mm	0.8 mg/dm^2	0.07 mg/dm^2
2	Other articles which can be filled	4.0 mg/l	0.3 mg/l
3	Cooking ware; packaging and storage vessels having a capacity of more than three litres	1.5 mg/l	0.1 mg/l

*2 According to Austrian Ceramic Ordinance (BGBl. Nr. 893/1993 and its amendment), articles in contact with food should not exceed the following limits:

Category	Description	Zinc	Antimony	Barium
Internal volume	Less than one litre	3.0 mg/article(#)	1.0 mg/article(#)	1.0 mg/article(#)
	Greater than one litre	3.0 mg/l	1.0 mg/l	1.0 mg/l

(#) Calculation is based on the internal volume of the article